# nextek 24D

Microencapsulated Phase Change Material Phase Change: 24°C, 75.2°F



**nextek** is the next level in PCM technology and performance. Nextek's patented capsule wall technology combines robustness, high thermal stability, and easy dispersability. It is versatile enough to be used in a variety of uses and formulations.

#### **APPLICATIONS**

The applications for phase change materials are limited only by the imagination. Some common uses for nextek PCM at this temperature include:

- Bedding to provide desired human comfort requirements such as a cool touch effect to mattresses, pillows, and mattress ticking.
- **Building Materials** to increase the energy efficiency of residential and commercial buildings.
- Consumer Textiles to provide desired human comfort requirements such as cool touch effect to fabrics or the ability to keep people cool when material is worn close to the body. nextek has helped companies achieve Oeko-Tex® Standard 100 Class I certification.

### **PACKAGING**

Dry powder is generally shipped in 55-gallon fiber drums of 140 pounds net weight or in super sacks of 650 pounds.

## **HEALTH AND SAFETY**

Please refer to the Safety Data Sheet (SDS) for necessary safety and handling precautions for this product.

#### **PROPERTIES**

nextek 24D typically exhibits these general properties:

| Typical Properties   |                                   |
|----------------------|-----------------------------------|
| Appearance           | White to slightly off-white color |
| Form                 | Dry powder (≥ 97% solids)         |
| Particle size (mean) | 15-30 micron                      |
| Melting point        | 24°C, 75.2°F (±2°C)               |
| Heat of fusion       | ≥ 170 J/g                         |

**Visit www.microteklabs.com or call 937.236.2213** for more information on your thermal management needs.

IMPORTANT NOTE: This data has been compiled from testing that Microtek Labs believes reliable and is supplied for informational purposes only. Microtek Labs encourages purchasers to validate this data and the product's fitness for use in the purchaser's process by performing their own tests.

MT23-007 nextek 24D PDS © 2023 Microtek Laboratories, Inc. All Rights Reserved. All other trademarks are the properties of their respective owners.

MPDS3300-0052

Revision 3

Effective Date: 10/16/2023

