# wivtek 29

Microencapsulated Phase Change Material Phase Change: 29°C, 84.2°F



**vivtek** continues Microtek's excellence in PCM technology and performance. vivtek's patented capsule wall technology combines robustness, high thermal stability, and easy dispersability with a sustainable bio-based core – produced from agricultural sources, not petroleum.

#### **APPLICATIONS**

The applications for phase change materials are limited only by the imagination. Some common uses for vivtek PCM at this temperature include:

- Bedding to provide desired human comfort requirements such as a cool touch effect to mattresses, pillows, and mattress ticking.
- **Building Materials** to increase the energy efficiency of residential and commercial buildings.
- Consumer Textiles to provide desired human comfort requirements such as cool touch effect to fabrics or the ability to keep people cool when material is worn close to the body.

### **PACKAGING**

This product is generally shipped in either 55-gallon fiber drums of 245 pounds net weight (175 pounds nominal dry weight) or in super sacks of 1,000 pounds (approximately 750 pounds nominal dry weight).

### **HEALTH AND SAFETY**

Please refer to the Safety Data Sheet (SDS) for necessary safety and handling precautions for this product.

## **PROPERTIES**

vivtek 29 typically exhibits these general properties:

Typical Properties	
Appearance	White to slightly off-white color
Form	Wet cake (≥ 70% solids)
Particle size (mean)	14-24 micron
Melting point	29°C, 84.2°F
Heat of fusion	170 J/g

**Visit www.microteklabs.com or call 937.236.2213** for more information on your thermal management needs.

IMPORTANT NOTE: This data has been compiled from testing that Microtek Labs believes reliable and is supplied for informational purposes only. Microtek Labs encourages purchasers to validate this data and the product's fitness for use in the purchaser's process by performing their own tests.

MT23-009 vivtek 29 PDS © 2023 Microtek Laboratories, Inc. All Rights Reserved. All other trademarks are the properties of their respective owners.

MPDS3300-0068

Revision 4

Effective Date: 03/05/2024

